

Technical Data – Argelite-H

<u>sizes</u>	length:	max. l = 800 mm (centre to centre distance) tolerance $\pm 1,0$ mm	
	height:	200 / 250 / 300 mm (centre to centre distance) tolerance $\pm 2,0$ mm	
	thickness:	24 mm tolerance $\pm 1,0$ mm	
<u>constancy of the form:</u> (DIN EN 1304)	wingity:	(<i>out of plane</i>)	$\pm 0,25$ % of the diagonal
	straightness:	(<i>in plane</i>)	$\pm 0,25$ % of the length/height
	evenness:	(<i>out of plane</i>)	$\pm 0,25$ % of the length
		(<i>out of plane</i>)	$\pm 0,70$ % of the height
	Angularity:	(<i>in plane</i>)	height ≤ 300 mm $\pm 1,0$ mm
<u>weight</u> (dry):	ca. 30 kg/m ²		
<u>body density:</u>	$\geq 2,0$ g/cm ³		
<u>breaking load:</u> (DIN EN 1304)	average value $\geq 12,8$ MPa		
<u>water absorption:</u> (DIN EN 539-2)	$\leq 9,0$ % according to test reports of Bautest Dresden GmbH (formerly MPA Dresden) between 3 and 8 %.		
<u>frost resistance:</u> (DIN EN 538-C)	50 frost and dew cycles average value $\geq 13,0$ MPa		
<u>linear thermal expansion:</u> (EN ISO 10545-8)	< 0.4 mm referring to a length of 1000mm		
<u>moisture expansion:</u> (DIN EN 10545-10)	= 0,03% (according to test reports of Bautest Dresden GmbH)		
<u>acid-resistance:</u> (DIN EN 10545-13)	proven (according to test reports of Bautest Dresden GmbH)		

alkali-resistance:
(DIN EN 10545-13)

proven (according to test reports of Bautest Dresden GmbH)

fire protection
classification:
(DIN 4102)

ceramic tile plates:
aluminium substructure:

flammability rating A, incombustible
flammability rating A1, incombustible

composition of clay:

calcspat
potash
quartz
feldspath
aluminium oxide
ferric oxide
manganese
chromium oxide
platinum

external control:

Bautest Dresden GmbH (formerly MPA Dresden); approved testing
laboratory, regulatory agency and certificate authority

04/2013